

(19)

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 867 963 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
30.09.1998 Bulletin 1998/40

(51) Int Cl.⁶: H01M 8/10, H01M 8/04

(21) Application number: 98302217.9

(22) Date of filing: 24.03.1998

(84) Designated Contracting States:
AT BE CH DE DK ES FI FR GB GR IE IT LI LU MC
NL PT SE
Designated Extension States:
AL LT LV MK RO SI

- Gamou, Takaharu
Fujieda City, 583-0026 (JP)
- Hatoh, Kazuhito
Daitou City, 574-0076 (JP)
- Yasumoto, Eichi
Katano City, 576-0021 (JP)

(30) Priority: 25.03.1997 JP 71814/97

(71) Applicant: Matsushita Electric Industrial Co., Ltd.
Kadoma-shi, Osaka 571-8501 (JP)

(74) Representative: Price, Paul Anthony King et al
D. Young & Co.,
21 New Fetter Lane
London EC4A 1DA (GB)


(72) Inventors:
• Gyoten, Hisaaki
Shijonawate City, 575-0013 (JP)

(54) Polymer electrolyte fuel cell

(57) The present invention is for facilitating removal of water around the catalytic layers (2) of a polymer electrolyte fuel cell and for providing a polymer electrolyte fuel cell which can prevent a drop in output performance caused by excessive wetting of electrode layers due to a long-hour operation or a large current outputting op-

eration. The polymer electrolyte fuel cell according to the present invention uses an electrode layer (7) having a water repellent porous base area and penetration areas which are higher in water permeability than in the base area. Such base area and penetration areas are formed as by imparting water repellency unevenly on a hydrophilic pore material, for example.

FIG. 1



EP 0 867 963 A2

Description

The present invention relates to a normal temperature-operating electrolyte fuel cell for use in such applications as a portable power source, an electric vehicle and a home power source system.

The normal temperature-operating polymer electrolyte fuel cell generates electricity by electrochemically reacting a fuel gas such as hydrogen and an oxidizer gas such as oxygen. The heat, which simultaneously comes out in the reaction, is also made good use of.

The basic construction composing a polymer electrolyte fuel cell is configured as in the following, for example. A polymer electrolyte film is made of a hydrogen ion conductive resin such as a fluorocarbon resin having a sulfo group. A catalytic layer substantially made of a carbon powder with a platinum group metal catalyst carried thereon is formed closely on each surface of the polymer electrolyte film. Furthermore, a gas-permeable and electrically conductive electrode layer is provided directly on the outer surface of each catalytic layer. On the outer surface of the electrode layer, an electrically conductive separator is provided to mechanically clamp the assembly composed of the electrode layers and the polymer electrolyte film and to electrically connect the assembly with the adjoining assembly in series. A groove-shaped channel to evenly supply the gas to the electrode layer is formed on the surface of the separator facing the electrode layer. The fuel gas is supplied to one of the pair of the electrode layers, and the oxidizer gas is supplied to the other. Hereafter described an arrangement in which hydrogen is used as the fuel gas and oxygen as the oxidizer gas.

A hydrogen gas supplied from outside is taken in the electrode layer on the hydrogen gas supplying side or the anode while passing along the surface of the electrode layer. The hydrogen gas taken in the electrode layer diffuses and passes through the electrode layer, then reaches the catalytic layer. When the hydrogen gas flows inside the catalytic layer and reaches a region where the polymer electrolyte coexists, an electrochemical reaction is caused between the hydrogen gas and the polymer electrolyte. The hydrogen gas is ionized by the reaction, and the generated hydrogen ions are taken into the polymer electrolyte film.

On the other hand, an oxygen gas supplied from outside is taken in the electrode layer on the oxygen gas supplying side or the cathode while passing along the surface of the electrode layer. The oxygen gas diffuses and passes through the electrode layer, then reaches the catalytic layer on the cathode side. Then, the oxygen gas turns into water vapor by reacting with hydrogen ions drifting from the anode through the electrolyte film. In this reaction, the electrons migrate from the anode to the cathode through an external load connected to the fuel cell. This migration of the electrons is utilized as an electric power. This electrochemical reaction between hydrogen and oxygen further produces heat. Therefore,

a cooling water is circulated through the inside of the fuel cell to keep the temperature of the fuel cell low, and the warmed water is utilized as a thermal energy.

The polymer electrolyte fuel cell is usually operated in a temperature range from a room temperature to about 80°C. Therefore, the water vapor generated by the electrochemical reaction on the catalytic layer on the cathode side mostly condenses into dew around the catalytic layer. When the condensed water remains around the catalytic layer, the oxygen gas is prevented from reaching the reaction area or the catalytic layer, and hence the cell performance is lowered. On the anode side, meanwhile, no water is generated. However, in a case the water generated on the cathode side permeates through the polymer electrolyte film and penetrates into the catalytic layer, or in a case the water vapor which is previously mixed into the fuel gas to prevent the electrolyte film from drying up condenses into dew and remains on the catalytic layer, the supply of hydrogen to the reaction area is blocked and the cell performance is dropped.

To solve the problems, various countermeasures have been proposed and tried, which include a water-repellent finish of the electrode layers to maintain the reaction area or the catalytic layers in a good wet condition, and an increased flow velocity of the gas flowing along the surface of the electrode layers so as to remove an excessive water sticking to the electrode layers.

However, the employment of the water repellent finished electrode layer causes a problem of hardly removing the water, resulting in a decreased cell performance, under some operating conditions as, for example, a high current density output operation which generates a large quantity of water or a low gas flow velocity operation. In some serious cases, the gas channels on the surfaces of the electrode layers are clogged, with the output of the cell dropping to zero.

It is an aim of the present invention to solve the foregoing problem and to provide a polymer electrolyte fuel cell which can facilitate a removal of water around the catalytic layer of the cell, thereby to prevent the cell performance from dropping due to excessive wetting of the electrode layer as in the long-hour operation or the high current density output operation.

The present invention provides a polymer electrolyte fuel cell comprising:

a plurality of assemblies, each assembly including a polymer electrolyte film with hydrogen ion conductivity and a pair of electrode layers sandwiching the polymer electrolyte film therebetween; and a plurality of electrically conductive separators, each separator being piled alternately with the assembly and including a gas supply channel to supply a gas to the electrode layer and a gas outlet channel for discharging a gas from the electrode layer, wherein the electrode layer comprises a porous base area with water repellency and a pene-

tration area higher in water permeability than in the base area.

In a preferred mode of the polymer electrolyte fuel cell of the present invention, the electrode layer is mainly composed of the porous base area and a plurality of the penetration areas which are scattered over the base area.

In another preferred mode of the polymer electrolyte fuel cell of the present invention, the penetration area is formed through the electrode layer.

The foregoing base area and penetration areas can be formed, for example, by adding water-repellency to a hydrophilic porous material unevenly and ununiformly. Most of the electrode layer surface is water repellent finished, however the scattering untreated areas or the penetration areas are also provided sparsely. The water repellent finish is carried out with a water repellent agent containing a fluorocarbon resin, for example.

While the prior art water repellent finish has been effected uniformly all over the surface of the electrode layer, the present invention uses the uneven water repellent finish to realize coexistence of the water-repellent area and the untreated areas in the porous material formed. This facilitates the oozing of water generated on the catalytic layer into the gas channels through the untreated areas. The random scattering of the wet spots or the water repellent areas wherein water lie stagnant and the gas-flowing spots or the untreated areas accelerates the gas flow velocity. This, it is considered, makes it easy to remove excessive water being stagnate within the electrodes.

The penetration areas can be formed of holes made by perforating through the electrode layer excepting the gas permeable pores originally possessed by the porous material. Since water tends to penetrate through larger openings in the water repellent porous material, the excessive water oozes through the formed holes. As a result, the removal of water by the gas flow is facilitated.

Even if the penetration areas are water repellent, in the case that the penetration areas has larger pores than those in the base area, water drops penetrate the pores in the penetration areas and thus the same results can be obtained.

When the penetration areas are arranged on the electrode layer so as to face the gas channel, more preferably along the center line of the gas channel where the gas flow velocity is high, water can be removed more efficiently thereby obtaining higher effects.

The present invention also provides a polymer electrolyte fuel cell comprising an electric generator including:

a plurality of assemblies, each assembly including a polymer electrolyte film with hydrogen ion conductivity and a pair of electrode layers sandwiching the polymer electrolyte film therebetween; and

a plurality of electrically conductive separators, each separator being piled alternately with the assembly and including a gas supply channel to supply a gas to the electrode layer and a gas outlet channel for discharging a gas from the electrode layer,

and further comprising a vibrator for applying a vibration to the electric generator.

In a preferred mode of the polymer electrolyte fuel cell according to the present invention, the vibrator is an ultrasonic vibrator which produces vibration intermittently or interlocked with the cell performance. Applying vibration with a relatively low frequency is more effective in removal of the water which overflows and blocks the gas channels than the water which blocks the permeable pores in the electrode. Vibration with a high frequency like ultrasonic, on the other hand, can remove the water which blocks the permeable pores in the electrode more efficiently.

The present invention further provides a polymer electrolyte fuel cell comprising an electric generator including:

a plurality of assemblies, each assembly including a polymer electrolyte film with hydrogen ion conductivity and a pair of electrode layers sandwiching the polymer electrolyte film therebetween; and a plurality of electrically conductive separators, each separator being piled alternately with the assembly and including a gas supply channel to supply a gas to the electrode layer and a gas outlet channel for discharging a gas from the electrode layer, and further comprising a gas compressor for intermittently compressing the gas to be supplied to the gas supply channel.

Since the velocity of the gases flowing along the catalytic and the electrode layers can be raised temporarily by providing a compressor on the gas supply means and by intermittently increasing the gas flow velocity, stagnating condensed water can be removed efficiently.

While the novel features of the invention are set forth particularly in the appended claims, the invention, both as to organization and content, will be better understood and appreciated, along with other objects and features thereof, from the following detailed description taken in conjunction with the drawings.

BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWING

FIG. 1 is a cross-sectional view showing the main part of the polymer electrolyte fuel cell in an embodiment of the present invention.

FIG. 2 is a characteristics diagram showing the change with time in the output voltage of the same pol-

polymer electrolyte fuel cell.

FIG. 3 is a characteristics diagram showing a change with time in an output voltage of a polymer electrolyte fuel cell in another embodiment of the present invention.

FIG. 4 is a characteristics diagram showing a change with time in an output voltage of a polymer electrolyte fuel cell in still another embodiment of the present invention.

DETAILED DESCRIPTION OF THE EMBODIMENTS

Preferred embodiments of the present invention are hereinafter described in detail with reference to the attached drawings.

EMBODIMENT 1

A carbon powder with a particle diameter of several μm was dipped in an aqueous solution of chloroplatinic acid. The carbon powder was then subjected to a reduction treatment to carry a platinum catalyst thereon. The ratio of the carbon powder to the carried platinum was 1 to 1 by weight. The carbon powder with platinum was then dispersed in an alcoholic solution of a polymer electrolyte to give a slurry.

Meanwhile, an aqueous dispersion of a fluorocarbon resin ("Neofreon ND-1" manufactured by Daikin Industries, Ltd., Japan) was applied by splashing onto the both surfaces of a carbon unwoven fabric with a thickness of 400 μm to be employed as an electrode so that the surfaces of the carbon unwoven fabric were coated unevenly with the fluorocarbon resin powder. The carbon unwoven fabric was then dried, followed by a heat treatment at 400°C to produce a carbon unwoven fabric electrode.

The obtained carbon unwoven fabric electrode as a whole showed water repellency when wetted with water, but the water penetrated inside in time. By a microscopic observation of the surface and the section of the carbon unwoven fabric electrode, it was confirmed that there were scattered regions 30 μm to several mm in width where no fluorocarbon resin is applied.

In parallel with that, the same kind of carbon unwoven fabric was uniformly coated with the aqueous dispersion of the fluorocarbon resin and heat-treated. When this unwoven fabric was wetted with water, large water drops were formed on the surface of the unwoven fabric and would not penetrate inside even in part.

One surface of each carbon unwoven fabric electrode thus water repellent finished was coated uniformly with the aforementioned slurry containing carbon powder and then dried to form a catalytic layer. A polymer electrolyte film 1 with a thickness of 50 μm made of a fluorocarbon resin having a sulfo group was sandwiched between two pieces of the carbon unwoven fabric electrodes 7 so placed as to face the catalytic layer 2 each other. They were then dried to obtain an assembly 9

shown in FIG. 1. The carbon unwoven fabric electrodes 7 were 5 cm in length and width, while the polymer electrolyte film 1 was 8 cm in length and width. The carbon unwoven fabric electrodes 7 were put in the center of the polymer electrolyte film 1. In the assembly 9 thus obtained, it was confirmed that the polymer electrolyte film 1 and the carbon unwoven fabric electrode 7 were firmly bonded each other via the catalytic layer 2 where the platinum-carrying carbon powder and the polymer electrolyte coexisted.

The assemblies 9 and an airtight carbon separator plates 5 were piled alternately to give a three-cell unit as shown in FIG. 1. The separator plate 5 was 4 mm in thickness and has a plurality of channels 4 of 1 mm in width and depth, provided in one direction by cutting the surface thereof. A seal material 8 was interposed between the separator plate 5 and the polymer electrolyte 1 to provide an electrical insulation therebetween and to prevent leakage of the gases inside.

End plates, which also serve as cooling plates, were placed on the both ends of the piled cells and the three cells were pressed and clamped under a pressure of 10 kgf/cm^2 in the piled direction. Characteristics tests were carried out with thus obtained three-cell unit as follows. A hydrogen gas as a fuel gas was supplied to the anode with the utilization of 60%. On the other hand, an air as an oxidizer gas was supplied to the cathode with the utilization of 20%. A temperature controller was provided on each gas supply unit, which was so set that the temperature of the supply gas was, in principle, identical with that of the cell. A humidifier is also provided on each gas supply unit, and the humidity was so adjusted that the dew point of the supply gas was 15 to 35°C lower than the cell temperature.

FIG. 2 shows the characteristics change with time when the three-cell unit of the present embodiment was operated with an output current density of 300 mA/cm^2 . FIG. 2 also shows the characteristics of the prior art three-cell unit with the uniformly water repellent finished electrodes as a comparative example. The output voltage of the comparative example dropped sharply 30 minutes after the start of operation and ran out of power some 60 minutes later. The three-cell unit of the present embodiment, on the other hand, maintained the performance high for a long time though the output dropped slightly in the initial stage.

EMBODIMENT 2

Another method of providing the electrode layers with an uneven water repellent finish will be described in the present embodiment.

A paraffin powder with a melting point of 60 to 90°C and a particle diameter of 0.01 to 0.2 mm was scattered over the surface of a carbon unwoven fabric 400 μm in thickness. The unwoven fabric was then stored for 30 minute in a thermostatic chamber maintained at 120°C. The paraffin powder scattered on the unwoven fabric

melted and penetrated into the unwoven fabric by the heat treatment. The unwoven fabric was then taken out of the thermostatic chamber and was allowed to cool to a room temperature. An observation of this unwoven fabric confirmed penetrations of paraffin in the shape of cylinder 0.02 to 1 mm in diameter through the unwoven fabric.

This unwoven fabric was dipped in the same aqueous dispersion of fluorocarbon resin powder as used in Embodiment 1 and dried. The material was then subjected to a heat treatment for some one hour at 400°C. Paraffin evaporates in the initial stage of such heat treatment, and the fluorocarbon resin powder which has stuck to the unwoven fabric by the dipping peels off in the heat treatment. Thus, the areas where paraffin stuck on the unwoven fabric are left uncoated with fluorocarbon resin in the heat treatment. On the areas with no paraffin, on the other hand, the fluorocarbon resin powder sticks directly to the unwoven fabric when the material is dipped in the dispersion. The fluorocarbon resin sticking directly to the fabric melts thereby forming a water repellent coating on the unwoven fabric by the heat treatment. In the unwoven fabric thus treated, the water repellent areas and the highly wettable areas coexist, each extending from one surface to the other.

When the treated unwoven fabric was actually wetted with water on the surface, it was confirmed that water passed from one side to the other through the highly wettable areas where no fluorocarbon resin was coated. A three-cell unit was assembled using the water repellent finished unwoven fabric in the same manner as in Embodiment 1. The obtained three-cell unit was operated with an output current density of 300 mA/cm² in the same way as in Embodiment 1. As a result, a stable output voltage continued for not shorter than 1,000 minutes.

EMBODIMENT 3

In the present embodiment, there will be explained a method of controlling the water permeability of the electrode layer through the pore diameter of a water repellent porous material.

A carbon unwoven fabric 400 µm in thickness was coated with fluorocarbon resin by dipping in the same aqueous dispersion of fluorocarbon resin powder as used in Embodiment 1. The unwoven fabric was then heat-treated for some one hour at 400°C to form a fluorocarbon resin coating on the surface.

The unwoven fabric thus uniformly water repellent finished was roughly loosened into small pieces. These small pieces were immersed into an aqueous solution containing proper amounts of a surfactant and carboxymethylcellulose as a binder, then the solution was stirred. When the solution was stirred, some of the unwoven fabric pieces broke up into single fibers, but other fibers remained in lumps.

Those fibers were refabricated into a unwoven fab-

ric. The remade unwoven fabric had two types of regions, dense regions made up of fibers that had not been dispersed by the foregoing stirring and coarse regions formed of fibers that had been dispersed apart by the stirring and reassembled.

In water repellent porous materials as the aforementioned unwoven fabric, the water permeability depends on the diameter of pores on the surface. That is to say, the larger the diameter, the easier the water penetration. In the foregoing unwoven fabric, the water permeability on the coarse regions is higher than that on the dense regions, and water sticking to the surface of such porous material tends to move toward the coarse regions.

A polymer electrolyte fuel cell was assembled using the remade unwoven fabric in the same manner as in Embodiment 1. The three-cell unit obtained was operated with an output current density of 300 mA/cm² in the same way as in Embodiment 1. A stable output voltage continued for not shorter than 1,000 minutes. That is, it was confirmed that the water generated by the electrode reaction and the condensed water can be removed through the coarse regions on the electrode layer.

EMBODIMENT 4

In the present embodiment, there will be explained a method of facilitating the removal of water generated on the catalytic layers by forming holes therethrough.

Carbon unwoven fabrics were uniformly water repellent finished by dipping in the same aqueous dispersion of fluorocarbon resin powder as used in Embodiment 1. Then, a plurality of fine through holes were formed in the carbon unwoven fabrics using a carbonic acid gas laser. Four kinds of three-cell units were assembled using the unwoven fabrics, each with a different hole size and hole arrangement, in the same manner as in Embodiment 1. Cell unit "A" was assembled using the carbon unwoven fabrics with 3 to 5 holes/cm², each 50 µm in diameter, cut randomly on the surface. Cell unit "B" was assembled using the carbon unwoven fabrics on which 50 µm-diameter holes were formed along the center line of the opposite gas channel of the separator plate at an interval of 3 mm. Cell unit "C" was assembled using the same carbon unwoven fabrics as used in Cell unit "A" but has the hole diameter of 100 µm. Cell unit "D" was assembled using the same carbon unwoven fabric as used in Cell unit "B" but has the hole diameter of 100 µm. It is noted that the hole diameter was so chosen as to be some 10 times the diameter of the carbon fiber used in the carbon unwoven fabric.

The four kinds of three-cell units were tested with regard to the change with time in characteristics. The results are illustrated in FIG. 3.

As shown in FIG. 3, all of the three-cell units in the present embodiment exhibited a long and stable output voltage unlike the comparative cell units using unwoven fabrics with no perforated hole. FIG. 3 shows the char-

acteristics changes at a current density of 300 mA/cm², a hydrogen utilization of 60% and an air utilization of 20%.

When the three-cell units were tested at a current density of 500 mA/cm² with a hydrogen utilization of 60%, especially good results were obtained with Cell unit "B" and Cell unit "D" which had been assembled with the carbon unwoven fabrics on which the through holes were formed regularly along the center line of the gas channels of the opposite separator plate. It was also indicated that Cell unit "C" with the fabrics with 100 μ m-diameter holes gave better results than Cell unit "D" with the unwoven fabric with 50 μ m-diameter holes. That is probably because with rise in current density or utilization, the flow velocity of the gas that carries away water decreases in relation to the generation rate of water to be removed, and large holes can eliminate the water more efficiently.

EMBODIMENT 5

In the present embodiment, there will be explained a method of facilitating the discharging the water generated on the catalytic layer out of the unit by applying vibration to the cell.

Three cells of the prior art used as comparison example in Embodiment 1 were piled. A pair of metal end plates were provided on the both ends of this laminate. The end plates were then connected to each other via connecting members so as to compress the cells. Thus a three-cell unit (with an electrode area of 100 cm²) was obtained. The three-cell unit thus obtained was mounted on a mechanical vibrator stand and then vibrated continuously or intermittently at a rate of 1 to 50 cycles per second.

Separately, to apply vibration of a higher frequency, an ultrasonic vibration plate employing an ultrasonic piezoelectric transducer (output of 50 W) was screwed to the end plates of a similar three-cell unit. As an electrically insulating plate, an acrylic resin plate which was right, hard and low in sound wave attenuation was interposed between the end plate and the three-cell unit in order to use the ultrasonic efficiently for eliminating the generated water. An electric circuit to adjust the magnitude and output time of the ultrasonic piezoelectric transducer was also mounted on an ultrasonic piezoelectric transducer.

The three-cell unit was supplied with a hydrogen gas and an air in such a way that the utilization of the hydrogen gas on the anode side was 60% and the air utilization on the cathode side was 20%. A temperature controller and a humidifier were provided on each gas supply unit, which were so set that the temperature of the supply gas was identical with that of the cell and the dew point of the supply gas was 15 to 35°C lower than the temperature of the cell unit.

FIG. 4 shows the changes in the output voltage of the three-cell units provided with the vibrator during a

relatively short time period.

As outputting continued at a current density of 300 mA/cm², the output voltage of the three-cell unit of the comparative example with no vibrator dropped sharply 30 minutes after start of operation, and the three-cell unit was exhausted some 60 minutes later. It is shown in comparison that the three-cell units of the present embodiment all improved in performance as vibration was applied. The prior three-cell unit as the comparative example continued to fall in output voltage with the lapse of time. On the other hand, the three-cell units of the present embodiment which were vibrated on the vibration stand fell in performance in the initial stage but reached a normal state in certain stages. This effect was more remarkable with a higher vibration frequency. The system of applying vibration of a relatively low frequency on such a mechanical vibrator stand, it appears, is not so effective in removing the water which blocks the gas permeable pores on the electrode but can effectively eliminate the water which overflows and blocks the gas channels.

Applying ultrasonic to the three-cell unit was very effective in facilitating the removal of the water. Especially the three-cell unit which was subjected to continuous ultrasonic vibration showed little fall in performance from immediately after the start of operation. This indicates that vibrations of a high frequency are more effective in eliminating the water which blocks the gas permeable pores on the electrode. It was also found that the performance of the three-cell unit in which the ultrasonic piezoelectric transducer was activated on and off or intermittently fell slightly when the piezoelectric transducer was stopped but soon recovered after the transducer was restarted. Considering the energy efficiency, noise, mechanical wear of the cell unit by vibration and other factors, therefore, the system of activating the piezoelectric transducer intermittently is more attractive for practical application.

EMBODIMENT 6

In the present embodiment, there will be explained a method of facilitating the removal of the water stagnating around the catalytic layers and the electrode layers by intermittently increasing the pressure of the gas supplied to the cell.

A three-cell unit (with an electrode area of 100 cm²) assembled by piling three of the same cells as used as comparison example in Embodiment 1 was mounted with a cylinder pump (cylinder volume of 1,000 cm³) to a gas pipe for supplying the anode gas and to the other gas pipe for supplying the cathode gas so that each gas taken in the cylinder pump could be discharged into the gas pipe instantly and intermittently. In addition, a gas check valve was mounted on the upstream side of cylinder pump on each gas pipe, so that pressure might be effectively felt in the three-cell unit with no reverse flow of the gas discharged from the cylinder pump. A pres-

sure sensor was provided near each joint to the cell unit, and an electrical drive unit interlocked with the pressure sensor for driving the cylinder pump to apply pressure on the gas was mounted on the cylinder pump.

The three-cell unit equipped with that pressure application unit was tested to examine the change with time in characteristics. When the pressure application unit was not activated, the three-cell units of the present embodiment fell in performance too much to run any more some 60 minutes after the start in the continuous operation at a current density of 300 mA/cm² as in the case with the prior three-cell unit. But when a pressure of 5,000 to 10,000 Pa was applied for 0.5 seconds at an interval of 10 minutes, the three-cell units recovered the original performance each time. This indicates that intermittent compression of the supply gas increased temporarily the flow velocity of the gas flowing in the catalytic layers and the electrode layers, thereby eliminating the stagnating water.

In the above embodiment, the application of pressure on the anode side was synchronized with that on the cathode side in consideration of possible damages on the cell such as breakage of the film. But the two sides can be compressed independently of each other. Also, the application of pressure can be confined to the anode side or the cathode side alone with good results.

As to the time of applying pressure, it was found that 0.5 to 1.0 seconds was enough for the three-cell units used in the above embodiment to recover the original output characteristics. It appears that the time depends on the internal configuration of the cell system. Therefore, the duration of applying pressure is freely chosen for different cell unit configurations. The pressure to be applied is also decided on taking into consideration the internal structure of the cell unit and other factors.

In the present embodiment, it is further noted, a gas cylinder pump was used as means for applying pressure. Other means can be used instead, including a system consisting of an auxiliary gas cylinder and an electromagnetic valve.

As described, the present invention can effectively remove out of the cell unit the water stagnating around the catalytic layers and the electrode layers of the fuel cell, ensuring smooth supply of oxygen to the reaction area on the catalytic layers. Thus, the present invention provides a fuel cell which can maintain the performance at a high level for a long time.

Although the present invention has been described in terms of the presently preferred embodiments, it is to be understood that such disclosure is not to be interpreted as limiting. Various alterations and modifications will no doubt become apparent to those skilled in the art to which the present invention pertains, after having read the above disclosure. Accordingly, it is intended that the appended claims be interpreted as covering all alterations and modifications as fall within the scope of the invention.

Claims

1. A polymer electrolyte fuel cell comprising:

a plurality of assemblies, each assembly including a polymer electrolyte film with hydrogen ion conductivity and a pair of electrode layers sandwiching said polymer electrolyte film therebetween; and
a plurality of electrically conductive separators, each separator being piled alternately with said assembly and including a gas supply channel to supply a gas to said electrode layer and a gas outlet channel for discharging a gas from said electrode layer, wherein said electrode layer comprises a porous base area with water repellency and a penetration area higher in water permeability than in said base area.

2. The polymer electrolyte fuel cell in accordance with claim 1, wherein said electrode layer is mainly composed of said porous base area and a plurality of said penetration areas are scattered over said base area.

3. The polymer electrolyte fuel cell in accordance with claim 1, wherein said penetration area is formed through said electrode layer.

4. The polymer electrolyte fuel cell in accordance with claim 1, wherein said penetration area is made of a hydrophilic porous material and said base areas is made of a porous material provided with water repellency.

5. The polymer electrolyte fuel cell in accordance with claim 4, wherein said water repellency is provided by coating with a water repellent agent containing a fluorocarbon resin.

6. The polymer electrolyte fuel cell in accordance with claim 1, wherein said penetration area is a hole formed by perforating said electrode layer.

7. The polymer electrolyte fuel cell in accordance with claim 1, wherein said penetration area is provided at a portion on said electrode layer facing to said gas supply channel or said gas outlet channel of the opposite electrically conductive separator.

8. The polymer electrolyte fuel cell in accordance with claim 1, wherein said penetration area comprises a water repellent pore larger in diameter than those on said base area.

9. A polymer electrolyte fuel cell comprising an electric generator including:

a plurality of assemblies, each assembly including a polymer electrolyte film with hydrogen ion conductivity and a pair of electrode layers sandwiching said polymer electrolyte film therebetween; and 5
a plurality of electrically conductive separators, each separator being piled alternately with said assembly and including a gas supply channel to supply a gas to said electrode layer and a gas outlet channel for discharging a gas from 10
said electrode layer,
and further comprising a vibrator for applying vibration to said electric generator.

10. The polymer electrolyte fuel cell in accordance with claim 9, wherein said vibrator is an ultrasonic vibrator arranged in contact with said electric generator. 15

11. The polymer electrolyte fuel cell in accordance with claim 10, wherein said ultrasonic vibrator produces said vibration intermittently or interlocked with an output of said electric generator. 20

12. A polymer electrolyte fuel cell comprising an electric generator including: 25

a plurality of assemblies, each assembly including a polymer electrolyte film with hydrogen ion conductivity and a pair of electrode layers sandwiching said polymer electrolyte film therebetween; and 30
a plurality of electrically conductive separators, each separator being piled alternately with said assembly and including a gas supply channel to supply a gas to said electrode layer and a gas outlet channel for discharging a gas from 35
said electrode layer,
and further comprising a gas compressor for intermittently compressing said gas to be supplied to said gas supply channel. 40

45

50

55

FIG. 1




FIG. 2




FIG. 3





FIG. 4



(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 867 963 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
04.09.2002 Bulletin 2002/36

(51) Int Cl.7: **H01M 8/10, H01M 8/04**

(43) Date of publication A2:
30.09.1998 Bulletin 1998/40

(21) Application number: **98302217.9**

(22) Date of filing: **24.03.1998**

(84) Designated Contracting States:
**AT BE CH DE DK ES FI FR GB GR IE IT LI LU MC
NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

- Gamou, Takaharu
Fujiedera City, 583-0026 (JP)
- Hatoh, Kazuhito
Daitou City, 574-0076 (JP)
- Yasumoto, Eichi
Katano City, 576-0021 (JP)

(30) Priority: **25.03.1997 JP 7181497**

(71) Applicant: **Matsushita Electric Industrial Co., Ltd.**
Kadoma-shi, Osaka 571-8501 (JP)

(74) Representative: **Price, Paul Anthony King et al**
D. Young & Co.,
21 New Fetter Lane
London EC4A 1DA (GB)


(72) Inventors:
• Gyoten, Hisaaki
Shijonawate City, 575-0013 (JP)

(54) Polymer electrolyte fuel cell

(57) The present invention is for facilitating removal of water around the catalytic layers (2) of a polymer electrolyte fuel cell and for providing a polymer electrolyte fuel cell which can prevent a drop in output performance caused by excessive wetting of electrode layers due to a long-hour operation or a large current outputting op-

eration. The polymer electrolyte fuel cell according to the present invention uses an electrode layer (7) having a water repellent porous base area and penetration areas which are higher in water permeability than in the base area. Such base area and penetration areas are formed as by imparting water repellency unevenly on a hydrophilic pore material, for example.

FIG. 1



EP 0 867 963 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 98 30 2217

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cls)
X	US 5 607 785 A (TOZAWA TAKESHI ET AL) 4 March 1997 (1997-03-04) * column 2, line 23 - line 38; claims 1,2; figures 3,5 * * column 6, line 8 - line 27 * * column 7, line 7 - line 38 *	1-3,6,7	H01M8/10 H01M8/04
X	DATABASE WPI Section Ch, Week 8543 Derwent Publications Ltd., London, GB; Class A85, AN 85-267637 XP002071064 -& JP 60 181292 A (JAPAN STORAGE BATTERY CO LTD) * abstract * -& PATENT ABSTRACTS OF JAPAN vol. 10, no. 31 (C-327), 6 February 1986 (1986-02-06) & JP 60 181292 A (NIHON DENCHI KK), 14 September 1985 (1985-09-14) * abstract *	1,2,7	
X	PATENT ABSTRACTS OF JAPAN vol. 016, no. 162 (E-1192), 20 April 1992 (1992-04-20) -& JP 04 012462 A (FUJI ELECTRIC CO LTD), 17 January 1992 (1992-01-17) * abstract * -& CHEMICAL ABSTRACTS, vol. 116, no. 22, 1 June 1992 (1992-06-01) Columbus, Ohio, US; abstract no. 218125, NISHIHARA: "Solid polymer-electrolyte fuel cells" XP002071062 * abstract * & JP 04 012462 A (FUJI ELECTRIC CO) 17 January 1992 (1992-01-17) --- -/--	1-5	TECHNICAL FIELDS SEARCHED (Int.Cls) H01M
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 15 May 2002	Examiner D'hondt, J
CATEGORY OF CITED DOCUMENTS X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document		T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons &: member of the same patent family, corresponding document	

EPO FORM 1503 03/82 (P4/CN1)



European Patent
Office

Application Number

EP 98 30 2217

CLAIMS INCURRING FEES

The present European patent application comprised at the time of filing more than ten claims.

☐ Only part of the claims have been paid within the prescribed time limit. The present European search report has been drawn up for the first ten claims and for those claims for which claims fees have been paid, namely claim(s):

☐ No claims fees have been paid within the prescribed time limit. The present European search report has been drawn up for the first ten claims.

LACK OF UNITY OF INVENTION

The Search Division considers that the present European patent application does not comply with the requirements of unity of invention and relates to several inventions or groups of inventions, namely:

see sheet B

☒ All further search fees have been paid within the fixed time limit. The present European search report has been drawn up for all claims.

☐ As all searchable claims could be searched without effort justifying an additional fee, the Search Division did not invite payment of any additional fee.

☐ Only part of the further search fees have been paid within the fixed time limit. The present European search report has been drawn up for those parts of the European patent application which relate to the inventions in respect of which search fees have been paid, namely claims:

☐ None of the further search fees have been paid within the fixed time limit. The present European search report has been drawn up for those parts of the European patent application which relate to the invention first mentioned in the claims, namely claims:



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 98 30 2217

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cls)
X	PATENT ABSTRACTS OF JAPAN vol. 095, no. 007, 31 August 1995 (1995-08-31) -& JP 07 105957 A (TOYOTA MOTOR CORP), 21 April 1995 (1995-04-21) * abstract * -& DATABASE WPI Derwent Publications Ltd., London, GB; AN 95188591 XP002071065 * abstract * -& CHEMICAL ABSTRACTS, vol. 123, no. 8, 21 August 1995 (1995-08-21) Columbus, Ohio, US; abstract no. 88396, KAWAZU: "Electrochemical devices, especially solid electrolyte fuel cells" XP002071063 * abstract *	1,4	
X	US 5 364 711 A (HASIMOTO KOJI ET AL) 15 November 1994 (1994-11-15) * column 39, line 50 - column 40, line 32; claim 20; figures 22,24 *	9,10	TECHNICAL FIELDS SEARCHED (Int.Cls)
P,X	WO 98 04014 A (PREIDEL WALTER ;SIEMENS AG (DE)) 29 January 1998 (1998-01-29) * page 4, line 31 - page 5, line 8; claims 1,5 *	9-11	
Y	PATENT ABSTRACTS OF JAPAN vol. 1996, no. 01, 31 January 1996 (1996-01-31) -& JP 07 235324 A (TOYOTA MOTOR CORP), 5 September 1995 (1995-09-05) * abstract *	12	
The present search report has been drawn up for all claims			
Place of search		Date of completion of the search	Examiner
THE HAGUE		15 May 2002	D'hondt, J
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03/82 (P4/C01)



European Patent
Office

**LACK OF UNITY OF INVENTION
SHEET B**

Application Number
EP 98 30 2217

The Search Division considers that the present European patent application does not comply with the requirements of unity of invention and relates to several inventions or groups of inventions, namely:

1. Claims: 1-8

Polymer electrolyte fuel cell with electrode layer avoiding flooding by the water product

2. Claims: 9-12

Polymer electrolyte fuel cell comprising means for facilitating the removal of the water product



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 98 30 2217

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.C1.6)
Y	EP 0 716 463 A (TOYOTA MOTOR CO LTD) 12 June 1996 (1996-06-12) * claims 15-19 *	12	
Y	EP 0 073 044 A (HITACHI LTD) 2 March 1983 (1983-03-02) * claims 8,9; figure 4 *	12	
P,Y	PATENT ABSTRACTS OF JAPAN vol. 1998, no. 04, 31 March 1998 (1998-03-31) -& JP 09 312168 A (TOYOTA MOTOR CORP), 2 December 1997 (1997-12-02) * abstract *	12	
X	PATENT ABSTRACTS OF JAPAN vol. 012, no. 017 (E-574), 19 January 1988 (1988-01-19) -& JP 62 176064 A (HITACHI LTD), 1 August 1987 (1987-08-01) * abstract *	12	
X	US 5 366 821 A (BLAIR JAMES D ET AL) 22 November 1994 (1994-11-22) * claims 1-3,9; figure 3 * * column 1, line 49 * * column 2, line 44 - line 58 * * column 4, line 22 - line 35 * * column 9, line 24 - line 53 *	12	
A	PATENT ABSTRACTS OF JAPAN vol. 012, no. 355 (E-661), 22 September 1988 (1988-09-22) -& JP 63 110558 A (HITACHI LTD), 16 May 1988 (1988-05-16) * abstract *	12	
			TECHNICAL FIELDS SEARCHED (Int.C1.6)
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 15 May 2002	Examiner D'hondt, J
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03 82 (P04031)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 98 30 2217

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
A	US 5 478 662 A (STRASSER KARL) 26 December 1995 (1995-12-26) * column 6, line 28 - line 60; claim 1; figure 1 *	12	
A	EP 0 560 295 A (HITACHI LTD) 15 September 1993 (1993-09-15) * page 2, line 50 - page 3, line 1; claim 1 * * page 4, line 14 - line 22; figure 1 * * page 4, line 48 - page 5, line 6; figure 2 *	1	
A	US 3 418 168 A (WENTWORTH RALPH L) 24 December 1968 (1968-12-24) * column 3, line 41 - line 69; figure 3 *		
A	DE 33 23 491 A (GEN ELECTRIC) 12 January 1984 (1984-01-12) * page 10, paragraph 2; figure 1 *		
A	AT 389 020 B (SCHUETZ PETER DIPL ING DR) 10 October 1989 (1989-10-10) * claim 17 *		
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
Place of search THE HAGUE		Date of completion of the search 15 May 2002	Examiner D'hondt, J
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1509 03/82 (P24C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 98 30 2217

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

15-05-2002

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5607785	A	04-03-1997	NONE	
JP 60181292	A	14-09-1985	JP 1473145 C JP 63020314 B	27-12-1988 27-04-1988
JP 04012462	A	17-01-1992	NONE	
JP 07105957	A	21-04-1995	NONE	
US 5364711	A	15-11-1994	JP 6188008 A US 5432023 A	08-07-1994 11-07-1995
WO 9804014	A	29-01-1998	DE 19628888 C1 WO 9804014 A1	15-01-1998 29-01-1998
JP 07235324	A	05-09-1995	NONE	
EP 0716463	A	12-06-1996	JP 8138697 A JP 8167421 A EP 0716463 A2 EP 0911899 A2 KR 171207 B1 US 5939218 A	31-05-1996 25-06-1996 12-06-1996 28-04-1999 30-03-1999 17-08-1999
EP 0073044	A	02-03-1983	JP 58034574 A DE 3274930 D1 EP 0073044 A2 US 4612261 A	01-03-1983 05-02-1987 02-03-1983 16-09-1986
JP 09312168	A	02-12-1997	NONE	
JP 62176064	A	01-08-1987	NONE	
US 5366821	A	22-11-1994	AU 671628 B2 AU 3880493 A CA 2131387 A1 WO 9318556 A1 DE 69302902 D1 DE 69302902 T2 EP 0630528 A1 JP 2854138 B2 JP 7505011 T	05-09-1996 05-10-1993 16-09-1993 16-09-1993 04-07-1996 12-12-1996 28-12-1994 03-02-1999 01-06-1995
JP 63110558	A	16-05-1988	NONE	
US 5478662	A	26-12-1995	CA 2102359 A1	06-05-1994

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 98 30 2217

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

15-05-2002

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5478662	A		DE 59306256 D1	28-05-1997
			EP 0596366 A1	11-05-1994
			ES 2101920 T3	16-07-1997
			JP 6203862 A	22-07-1994
			US RE36148 E	16-03-1999
EP 0560295	A	15-09-1993	JP 3245929 B2	15-01-2002
			JP 5251086 A	28-09-1993
			DE 69302931 D1	11-07-1996
			DE 69302931 T2	10-10-1996
			EP 0560295 A1	15-09-1993
			US 5500292 A	19-03-1996
US 3418168	A	24-12-1968	NONE	
DE 3323491	A	12-01-1984	US 4543303 A	24-09-1985
			DE 3323491 A1	12-01-1984
			JP 1741333 C	15-03-1993
			JP 4025674 B	01-05-1992
			JP 59037663 A	01-03-1984
AT 389020	B	10-10-1989	AT 215286 A	15-02-1989

EPOFORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

THIS PAGE BLANK (USPTO)